

MM Kwidzyn Sp. z o.o.
 ul. Lotnicza 1
 82-500 Kwidzyn
 Poland



KWIDZYN

TECHNICAL DATA SHEET

SPEED-E PREPRINT

Parameter	Standard	Unit	Measurement	
Substance	EN ISO 536	g/m ²	80 ± 2	90 ± 2
Thickness	ISO 534	µm	106 ± 3	116 ± 3
Moisture content	EN ISO 287	%	3,8 - 5,2	3,8 - 5,2
Whiteness	ISO 11475	CIE units	166 ± 2	166 ± 2
Opacity	ISO 2471	%	94 +2/-1	95 +2/-1
Bendtsen Roughness	ISO 8791-2	ml/min	180 ± 50	180 ± 50
Cobb ₆₀	EN ISO 535	g/m ²	≤30	≤30

Certification

✓ 100% ECF Fibres

The data presented can be changed without notice.